




RCQ. MALTA-S
RCQ. MALTA 02



R874




N7N7




R8R8




7474




74A2




1000




5874




5858




58CY




7410




N774




10EZ




H2H2




H244




H2CV




1010




10CE



10G1




4468




6868




CV14




1010




10CE




10G1




Z774



Z7Z7



Z718



1818

GENERAL FABRIC INFORMATION				
Quality Name	RCQ.MALTA-S	Design Name	RCQ.MALTA 02	
End-Use	INDOOR/OUTDOOR	Width (±2cm)	140 cm (55")	Weight 284 gr/mt²
Composition	%100 ROLEFIN	Specials		
PHYSICAL TESTS				
Test		Standarts	Results	
Abrasion End		EN ISO 12947-2	> 50000	
Wyzenbeek		ASTM D4157	70000	
Martindale-Pilling 2.000 Cycle		EN ISO 12945-2	5	
Brush Pilling		D3511-99A	5	
Test		Standarts	Warp	Weft
Seam Slippage		EN ISO 13936-2	3.5	3.2
Tear Strength		EN ISO 13937-3	180	111
Tensile Strength		EN ISO 13934-1	1420	942
Colour Fastness Rubbing		EN ISO 105-X12(Dry/Wet)	4/5	4/5
Colour Fastness Light		EN ISO 105-B04	7	
FLAMMABILITY TESTS				
Test		Standarts	Results	
Cigarette Test		BS 5852 PART 1 SOURCE 0	PASS	
Cigarette Test		EN 1021-1	PASS	
Cigarette Test		CALL 117	PASS	
Cigarette Test		NFPA 260	PASS	

REPELLENCY / CLEANABILITY TESTS		
Test	Standarts	Results
Bleach Cleanable Test	EN 20105 N 01	PASS
Bleach Cleanable Test	AATCC 101	PASS
Bleach Cleanable Test	ACT TM1.2020 PART 1	PASS
Sprey Test	EN ISO 4920	80
Liquid Repellency	AATCC 193	8
Oil Repellency	AATCC 118	4
Phenolic Yellowing	EN ISO 105-X18	4/5

CARE CODES		
Washable	Wash 30°C gentle cycle	Care symbols
Iron	Low iron at max 110°C	
Tumble dry	Do not tumble dry	
Bleach	Bleach can be used	
Dry clean P	Do not dry clean	

Our products fulfil the requirements of Annex XVII of REACH (incl. the use of azo-dyes, heavy metals, etc.) as well as the American requirement regarding total content of lead in children's articles)
 In stain repellent products, we always use human and environmental friendly C6 fluorocarbons. In FR treatment, we always use DecaBDE free FR compounds.
 The colours in production might slightly vary from this reference due to different lots in production.



OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100



SUSTAINABLE TEXTILES